

102-HC Standard Nozzle

Acetylene

- Koike Standard nozzle
- Suitable for both hand and machine cutting



Stock #	Thickness (mm)	tip #	Pressure (bar)		Consumption (NI/h)			Cutting speed (mm/min)
			Oxygen	Fuel gas	Cutting O ²	Preheat O ²	Fuel gas	
80011	5	00	1.5	0.2	690	410	370	-660
80012	5-10	0	2.0	0.2	1200	410	370	660-550
80013	10-15	1	2.5	0.2	2100	480	430	550-490
80014	15-30	2	3.0	0.20	3400	480	430	490-400
80015	30-40	3	3.0	0.20	4300	480	430	400-350
80016	40-50	4	3.5	0.3	6500	550	500	350-320
80017	50-100	5	4.0	0.3	11000	690	630	320-200
80018	100-150	6	4.0	0.4	15000	770	700	200-150
80019	150-250	7	4.5	0.4	22000	1060	960	150-80
80051	250-300	8	4.5	0.4	28000	1060	960	80-45

102-D5 High-speed Nozzle (5 bar)

Acetylene

- Divergent technology (5 Bar cutting oxygen)
- Stainless steel inner tube



Stock #	Thickness (mm)	tip #	Pressure (bar)		Consumption (NI/h)			Cutting speed (mm/min)
			Oxygen	Fuel gas	Cutting O ²	Preheat O ²	Fuel gas	
80201	-5	00	5.0	0.2	850	520	470	-700
80202	5-10	0	5.0	0.2	1600	520	470	700-625
80203	10-15	1	5.0	0.2	2400	600	550	625-550
80204	15-30	2	5.0	0.2	3600	600	550	550-475
80205	30-40	3	5.0	0.2	4800	600	550	475-425
80206	40-50	4	5.0	0.2	5600	750	680	425-350
80207	50-100	5	5.0	0.3	8800	860	780	350-250
80208	100-150	6	5.0	0.3	13500	950	860	250-175
80209	150-250	7	5.0	0.3	24000	1330	1210	175-90
80210	250-300	8	5.0	0.4	31000	1600	1450	90-60

102-D7 High-speed Nozzle (7 bar)

Acetylene

- Divergent technology (7 Bar cutting oxygen)
- Stainless steel inner tube



Stock #	Thickness (mm)	tip #	Pressure (bar)		Consumption (NI/h)			Cutting speed (mm/min)
			Oxygen	Fuel gas	Cutting O ²	Preheat O ²	Fuel gas	
80221	5	00	7.0	0.2	750	520	470	-750
80222	5-10	0	7.0	0.2	1100	520	470	750-680
80223	10-15	1	7.0	0.2	2500	600	550	680-600
80224	15-30	2	7.0	0.20	3800	600	550	600-500
80225	30-40	3	7.0	0.20	5400	600	550	500-450
80226	40-50	4	7.0	0.2	7300	750	680	450-400
80227	50-100	5	7.0	0.3	10000	860	780	400-260
80228	100-150	6	7.0	0.3	14000	950	860	260-180
80229	150-250	7	7.0	0.3	22000	1330	1210	180-100
80230	250-300	8	7.0	0.4	35000	1600	1450	100-70

402-ST For IK-82 series

Acetylene

- For IK-82 series cutting machine only.



Stock #	Thickness (mm)	tip #	Pressure (bar)		Consumption (NI/h)			Cutting speed (mm/min)
			Oxygen	Fuel gas	Cutting O ²	Preheat O ²	Fuel gas	
80082	5-10	0	2.0	0.2	1200	380	340	500-450
80083	10-15	1	2.5	0.2	2100	485	440	450-400
80084	15-30	2	3.0	0.2	3400	485	440	400-350
80085	30-40	3	3.0	0.2	4300	550	500	350-300
80086	40-50	4	3.5	0.25	6500	640	580	300-250
80087	50-100	5	4.0	0.3	11000	730	660	250-200